

### **PROCEEDINGS**

# **Rate Effect of Adhesive Wear Due to Asperity Plowing**

## Jianqiao Hu<sup>1,2,\*</sup>, Hengxu Song<sup>1</sup> and Xiaoming Liu<sup>1,2</sup>

- <sup>1</sup>State Key Laboratory of Nonlinear Mechanics, Institute of Mechanics, Chinese Academy of Sciences, Beijing, 100190, China
- <sup>2</sup>School of Engineering Science, University of Chinese Academy of Sciences, Beijing, 100049, China
- \*Corresponding Author: Jianqiao Hu. Email: jianqiaohu@imech.ac.cn

### **ABSTRACT**

Material wear between contact surfaces with relatively sliding can be related to the failure of elevated asperities at small scales. The asperity wear depends on various factors, including material properties, interfacial adhesion, and friction velocity. In this study, using a series of materials characterized by the modified coarse-grained potentials, we studied the rate effect of adhesive wear at the asperity level over a wide range of plowing conditions. The results showed that increasing plowing velocity leads to the transition of the wear mechanism from plasticity-induced asperity smoothing to the formation of fractured debris and thus breaks down the Archard wear law. For asperity wear dominated by plasticity, the wear rate decreases as the velocity increases; this is because the contact force during asperity collisions strongly depends on the plowing velocity, whereas the wear volume exhibits weak velocity dependence. As the plowing velocity increases, the fractured wear debris forms and dramatically increases wear volume and thus a larger wear rate. Furthermore, it was found that decreasing interfacial adhesion leads to a smaller wear volume and yet a higher contact force. Our findings provide insight into the velocity dependence of wear rate in the tribological test.

## **KEYWORDS**

Adhesive wear; rate effect; asperity plowing; molecular dynamics; wear debris

**Funding Statement:** This work is supported by the National Natural Science Foundation of China (No. 12172358, 11972347).

**Conflicts of Interest:** The authors declare that they have no conflicts of interest to report regarding the present study.

